Technical data STANDARD SIZES 1250x2500mm 2500x1250mm

AVAILABLE THICKNESS OF SOLID WOOD CORE:

Thickness (mm)	Number of plies(pcs)	Deviation (mm)	Density according to factory production control system of Paged Morąg (kg/m3)
13	5		
16	5		
18	5		
22	5		
25	5	-0.2 +0,4	550 - 650
28	5		
30	5		
36	7		
45	7		

RELEASE OF FORMALDEHYDE (EN 717-1)

BONDING QUALITY(EN 314-2) Class 2

FACE SCREW HOLDING (EN 320) 198,9 kgf

BENDING STRENGTH FOR BLOCKBOARD 16mm AND MODULUS OF ELASTICITY

Flexural strength / MOE:

Ĭ I	
Along	58 MPa / 6800 MPa
Across	40 MPa / 4800 MPa

DIMENSIONAL DEVIATION AS PER EN 315 & EN 324

	Length / Width	Deviation
	< 1000 mm	± 1 mm
ĺ	1000 - 2000 mm	± 2 mm
	> 2000 mm	± 3 mm

STRAIGHTNESS AND SQUARENESS DEVIATION **AS PER EN 315 & EN 324**

Deviation

Straightness	± 0,1% or ± 1 mm/m
Squareness	± 0,1% or ± 1 mm/m



BLOCKBOARD

Power of wood

Wood has been the most precious gem in the nature's collection. As a natural, durable and adaptable material wood has become a cornerstone of construction, housing, boat-building and furniture industries. With some many applications, wood must be treated with care and diligence reserved for highly precious raw materials. That's why we created Paged Blockboard - made from sustainably sourced Pinus Silvestris pine.



Diverse applications

Paged blockboard is a sustainable, durable and elegant product. This combination of attributes makes it a perfect fit where high standards of mechanical and physical properties, low weight, ease of machining and natural beauty are sought after.



PACKAGING






DOORS & WINDOWS

Made completely from natural materials, Paged Blockboard is a popular choice for furniture, fit out and interior design craftsmen. With unlimited scope for its final applications Paged Blockboard may be the product you desire. Contact us and we will be happy to assist with trials.

www.sklejkapaged.pl








Inside core from solid pine wood

Panel thickness from 13mm to 45mm (9 choices)





BEECH











*Offered upon request