

The mark of responsible forestry

Paged BeechPly

A unique face quality plywood panel, made of locally sourced beech offers its users superb rigidity, durability and the highest face sheet quality possible. It is highly recognized by furniture makers and designers around the world.

KEY BENEFITS AND APPLICATIONS

- Main applications include: furniture craftsmanship, furniture joinery, boat and yacht fitout, interior design, flooring and stair building and manufacturing
- Uniform and homogenous surface
- High resistance and durability
- Easy to machine
- Made in Poland

STANDARD SIZES* [mm]

1250/1500x2500 1250x1950/2200 2500x1250/1500

*Other formats available on request

NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal Thickness (mm)*	Number of plies (pcs)		Deviation im)	Weight (kg/m²)	Density avg. (kg/m³)
4,0	3	-0,5	+0,3	3,2	<u></u>
6,5	5	-0,6	+0,4	5,2	<u>-</u>
9	7	-0,7	+0,5	7,2	
12	9	-0,8	+0,6	9,6	
15	11	-0,9	+0,7	12	
18	13	-0,9	+0,7	14,4	
21	15	-1,0	+0,8	16,8	
24	17	-1,1	+0,9	19,2	
27	19	-1,8	+1,4	21,6	
30	21	-1,9	+1,5	24	

^{*}Other thicknesses and special construction available upon request

½ E1

DIMENSIONAL DEVIATION AS PER EN 315 & EN 324

Length/Width	Deviation		
< 1000 mm	± 1 mm		
1000 – 2000 mm	± 2 mm		
> 2000 mm	± 3 mm		

STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

D -- -- -- --

Class 1 Class 2 Class 3 Edge machining, CNC machining and drilling on request

 General Terms of Sales available from www.skleikapaged.pl

 Face veneer qualities according to EN 635-2 available from www.sklejkapaged.pl

^{**}As measured at 8-12% moisture content

RELEASE OF FORMALDEHYDE (EN 717-1) BONDING QUALITY (EN 314-2) MACHINING ADDITIONAL INFORMATION



