



The mark of

Paged Twin Form

Paged Twin Form is a high quality mixed-wood species plywood overlaid with purpose-designed phenolic films. It offers an upgrade in terms of resistance to water and durability when compared to imported softwood panels and allows its users to maximize the life of the product.

KEY BENEFITS AND APPLICATIONS

- Main application areas include: formwork, concrete prefabrication, boat bulkheads, transportation and packaging
- Strong and rigid
- Resistance to temperature fluctuations
- High bending strength and shear
- Made from responsibly sourced wood in Poland

STANDARD SIZES* [mm]

1250x2500 1220x2440

*Other formats available on request

DIMENSIONAL DEVIATION AS PER EN 315 & EN 324

Length/Width	Deviation
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm

STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

COATING

Film type	Phenolic
Thickness	167 g/m²
Colour	Dark brown

NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal Thickness Number of plies (mm)* (pcs) 9 5	•	Standard Deviation (mm)		Weight (kg/m²)	Density avg. (kg/m³)
	5	-0,7	+0,5	5,4	_
12	6	-0,8	+0,6	7,3	<u>-</u>
15	7	-0,8	+0,7	9,1	_
18	9	-1,0	+0,7	10,9	_
21	10	-1,0	+0,8	12,7	- 605**
24	11	-1,1	+0,9	14,5	
27	12	-1,7	+1,4	16,3	_
30	13	-1,9	+1,5	18,2	_
35	16	-1,4	+1,1	21,2	_
40	18	-1,6	+1,2	24,2	

^{*}Other thicknesses available upon request

^{**}As measured at 8-12% moisture content

RELEASE OF FORMALDEHYDE (EN 717-1)	

½ E1

BONDING QUALITY (EN 314-2)

Class 3

MACHINING

Edge machining, CNC machining and drilling on request

ADDITIONAL INFORMATION

- General Terms of Sales available from www.sklejkapaged.pl
- Declaration of Performance available from www.skleikapaged.pl
- Film-faced plywood in-house norms and standards available from www.sklejkapaged.pl
- Surface coating types: F/F.



