

DECLARATION OF CONFORMITY, No DoC-HW-01

1. Identification code of the product-type:

Structural hardwood or combi plywood, coated or uncoated, 9-50 mm.

2. Intended uses:

For uncoated and surface unprotected plywood as a structural component according to EN 636-2.

For coated and/or surface protected plywood as a structural component according to EN 636-3.

3. Manufacturer:

Paged Pisz Sp. z o.o.
ul. Kwiatowa 1
12-200 Pisz

Paged Morąg S.A.
ul. Mazurska 1
14-300 Morąg

5. System of AVCP:

AVCP system 2+

6a. Harmonized standard:

EN 13986:2004+A1:2015

Paged Pisz
ul. Kwiatowa 1
12-200 Pisz, Poland
UK 0836-CPR-21/F525

Paged Morąg
ul. Mazurska 1
14-300 Morąg, Poland
UK 0836-CPR-21/F526

Notified body

British Board Of Agrément (Approved body No 0836)
Bucknalls Lane
Watford
Hertfordshire WD25 9BA

7. Declared performance:

Hardwood plywood				
Essential characteristics	End use condition	min. thickness (mm)	Performance	
			Class (ex. floorings)	Class (floorings)
Reaction to fire	without an air gap behind the wood-based panel	9	D-s2, d0	D _{fl-s1}
	with a closed or an open air gap not more than 22 mm behind the wood-based panel	9	D-s2, d2	-
	with a closed air gap behind the wood-based panel	15	D-s2, d1	D _{fl-s1}
	with an open air gap behind the wood-based panel	18	D-s2, d0	D _{fl-s1}
	any	3	E	E _{fl}
Essential characteristics	Performance			
Water vapour permeability	Wet cup μ - 90 Dry cup μ - 220			
Release of formaldehyde	Class E1			
Content of pentachlorophenol (PCP)	None			
Airborne sound insulation	NPD			
Sound absorption α	Range	α		
	250-500 Hz	0,10		
	1000-2000 Hz	0,30		
Thermal conductivity λ (W/(mK))	0,17			
Bonding quality	Class 3			
Biological durability	Uncoated or coated and unprotected	Use class 2		
	Coated with protected edges	Use class 3		
Embedment strength	NPD			
Air permeability	NPD			
Racking resistance	NPD			
Density range (kg/m ³)	640-760			

Harmonized standard EN 13986+A1:2015

Nominal thickness	9	12	15	18	21	24	27	30	35	40	45	50
Essential characteristics	Performance											
Bending strength class acc. to EN 636												
II	F40			F35			F40					
⊥	F35			F30			F30					
Characteristic bending strength acc. to EN 636 (N/mm ²)												
f _m II	60			52			60					
f _m ⊥	52			45			45					
Characteristic compression strength	NPD											
Characteristic tension strength	NPD											
E class in bending MOE acc. to EN 636												
II	E80	E80	E80	E70	E70							
⊥	E50	E60	E70	E60	E50							
Mean MOE in bending acc. to EN 636 (N/mm ²)												
E _m II	7200	7200	7200	6300	6300							
E _m ⊥	4500	5400	6300	5400	4500							
Mean MOE in compression and tension	NPD											
Char. panel shear	NPD											
Char. planar shear	NPD											
Mean MOR in panel shear	NPD											
Mean MOR in planar shear	NPD											

Harmonized standard EN 13986+A1:2015

Combi plywood				
Essential characteristics	End use condition	min. thickness (mm)	Performance	
			Class (ex. floorings)	Class (floorings)
Reaction to fire	without an air gap behind the wood-based panel	9	D-s2, d0	D _{fl} -s1
	with a closed or an open air gap not more than 22 mm behind the wood-based panel	9	D-s2, d2	-
	with a closed air gap behind the wood-based panel	15	D-s2, d1	D _{fl} -s1
	with an open air gap behind the wood-based panel	18	D-s2, d0	D _{fl} -s1
	any	3	E	E _{fl}
Essential characteristics	Performance			
Water vapour permeability	Wet cup μ - 90 Dry cup μ - 220			
Release of formaldehyde	Class ½ E1			
Content of pentachlorophenol (PCP)	None			
Airborne sound insulation	NPD			
Sound absorption α	Range	α		
	250-500 Hz	0,10		
	1000-2000 Hz	0,30		
Thermal conductivity λ (W/(mK))	0,17			
Bonding quality	Class 3			
Biological durability	Uncoated or coated and unprotected	Use class 2		
	Coated with protected edges	Use class 3		
Embedment strength	NPD			
Air permeability	NPD			
Racking resistance	NPD			
Density range (kg/m³)	580-700			

Harmonized standard EN 13986+A1:2015


Nominal thickness	9	12	15	18	21	24	27	30	35	40	45	50
Essential characteristics	Performance											
Bending strength class acc. to EN 636												
II	F40			F35			F40					
⊥	F35			F30			F30					
Characteristic bending strength acc. to EN 636 (N/mm²)												
f _m II	60			52			60					
f _m ⊥	52			45			45					
Characteristic compression strength	NPD											
Characteristic tension strength	NPD											
E class in bending MOE acc. EN 636												
II	E80	E90	E80	E70	E70							
⊥	E50	E70	E70	E60	E60							
Mean MOE in bending acc. to EN 636 (N/mm²)												
E _m II	7200	8100	7200	6300	6300							
E _m ⊥	4500	6300	6300	5400	5400							
Mean MOE in compression and tension	NPD											
Char. panel shear	NPD											
Char. planar shear	NPD											
Mean MOR in panel shear	NPD											
Mean MOR in planar shear	NPD											

Harmonized standard EN 13986+A1:2015

Performance of this product, as identified above, is in conformity with the set declared performances and characteristics. This declaration of conformity is issued in accordance with Regulation EU No. 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Pisz, POLAND, 1st December 2022



Jarosław Wasiuk
Dyrektor Sprzedaży Eksportowej
Export Sales Director