Paged Form

(Softwood plywood covered with special craft-based paper)

Paged Form is made of thick veneer softwood panel covered on both sides with special craft-based paper impregnated with resins. The specific construction of the panel reinforces its durability and resistance, while the surface and strength of the overlay allows its user to achieve a spotless surface press.

The product is available in two versions: covered with kraft paper on both sides (MDO/MDO) or covered with kraft paper on one side and phenolic film on the other (MDO/F).

ZASTOSOWANIA I KORZYŚCI

- Main application areas include: formwork, pre-fabricated concrete elements, paving slabs and stones
- Smooth board surface
- Rigidity and moisture resistance
- Made in Poland

THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal Thickness (mm)*	Number of plies (pcs)	Standard Dev	iation min. (mm)	Standard Deviation max. (mm)	Weight (kg/m2)
15	5	-0,8	+0,7	8,8	
18	7	-1,0	+0,7	10,5	585**
21	8	-1,0	+0,8	12,3	

*Other thicknesses available upon request

**As measured at 8-12% moisture content

STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

COATING

Film type	Kraft paper impregnated with phenolic resin	
Thickness	390 g/m2	
Film type	Phenolic	
Thickness	167 g/m2	
Colour	Dark brown	

Our product is made of renewable resource. Our products are characterized by low carbon footprint and are produced from certified wood, thus respecting the natural environment and the local community. The information contained in this document is intended as a guideline only and comes without warranty. We reserve the right to amend product specification sheets without notice.



*Other formats available on request

STANDARD SIZES *

PER EN 315 & EN 324

Length/Width

1000 – 2000 mm

< 1000 mm

> 2000 mm



The mark of responsible forestry

DIMENSIONAL DEVIATION AS Wartość odchylenia

2500x1250

2440x1220

Deviation

±1 mm

± 2 mm

± 3 mm

RELEASE OF FORMALDEHYDE (EN 717-1)	BONDING QUALITY (EN 314-2)	MACHINING	ADDITIONAL INFORMATION
½ E1	Class 3	Edge machining, CNC machining and drilling on request	 General Terms of Sales available from www.sklejkapaged.pl. Declaration of Performance available from www.sklejkapaged.pl. Film-faced plywood in-house norms and standards available from www.sklejkapaged.pl.



Our product is made of renewable resource. Our products are characterized by low carbon footprint and are produced from certified wood, thus respecting the natural environment and the local community. The information contained in this document is intended as a guideline only and comes without warranty. We reserve the right to amend product specification sheets without notice.