

DECLARATION OF PERFORMANCE, No 2024/01/02-DoP-HSW FR-01

- 1. Identification code of the product-type:**
Structural hardwood plywood with birch face and softwood core, coated or uncoated, 9-40 mm.
- 2. Intended uses:**
For uncoated and surface unprotected plywood as a structural component according to EN 636-2.
For coated and/or surface protected plywood as a structural component according to EN 636-3.
- 3. Manufacturer:**
Paged Morąg S.A.
ul. Mazurska 1
14-300 Morąg
- 5. System of AVCP:**
AVCP system 2+
- 6a. Harmonized standard:**
EN 13986:2004+A1:2015, EN 13501-1:2019-02

Paged Morąg
ul. Mazurska 1
14-300 Morąg, Poland
0763-CPR-6085

Notified body

MPA Eberswalde - Materialprüfanstalt Brandenburg GmbH (Approved body No 0763)
Alfred-Möller-Straße 1
16225 Eberswalde
Germany

7. Declared performance:

Hardwood plywood with birch face and softwood core			
Essential characteristics	End use condition	min. thickness (mm)	Performance
Reaction to fire	Wood and wood-based panels and substrates of Euroclasses A1 or A2 at least 6 mm thick, having a density $\geq 1800 \text{ kg/m}^3$. Mechanically fixed against the substrate or against battens created a void.	9	Class (floorings)
			B _{fl} -s1
Essential characteristics	Performance		
Water vapour permeability	Wet cup μ - 70 Dry cup μ - 200		
Release of formaldehyde	Class E1		
Content of pentachlorophenol (PCP)	None		
Airborne sound insulation	NPD		
Sound absorption α	Range	α	
	250-500 Hz	0,10	
	1000-2000 Hz	0,30	
Thermal conductivity λ (W/(mK))	0,13		
Bonding quality	Class 3		
Biological durability	Uncoated or coated and unprotected	Use class 2	
	Coated with protected edges	Use class 3	
Embedment strength	NPD		
Air permeability	NPD		
Racking resistance	NPD		
Mean density (kg/m^3)	605		

Harmonized standard EN 13986+A1:2015

Nominal thickness	9	12	15	18	21	24	27	30	35	40
Essential characteristics	Performance									
Characteristic bending strength										
f_m II	21,3	20,4	36,5	35,1	32,2	33,0	30,1	29,3	30,2	
f_m I	28,5	33,1	39,3	25,3	31,6	30,5	25,9	27,4	27,0	
Characteristic compression strength	NPD									
Characteristic tension strength	NPD									
Mean MOE in bending										
E_m II	5327	5774	10317	9169	8531	7244	8419	8246	7940	
E_m I	6438	6541	11267	10404	9327	8357	8344	8317	8158	
Mean MOE in compression and tension	NPD									
Char. panel shear	NPD									
Char. planar shear	NPD									
Mean MOR in panel shear	NPD									
Mean MOR in planar shear	NPD									

Harmonized standard EN 13986+A1:2015

Performance of this product, as identified above, is in conformity with the set declared performances and characteristics. This declaration of performance is issued in accordance with Regulation EU No. 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Morąg, POLAND, 2nd January 2024



Jarosław Wasiuk
Dyrektor Sprzedaży Eksportowej
Export Sales Director