





The mark of

Paged Ultra Form

(specialty formwork plywood panel design to last longer and serve during multiple uses)

Specialty formwork plywood panel design to last longer and serve during multiple uses thus saving it's users time and money. Its superb mechanical properties combined with hard-wear coating provides for an ideal solution. Paged Ultra Form is resistant to UV lightening and chemical agents. It is perfect for vertical, special and frame formwork systems.

KEY BENEFITS AND APPLICATIONS

- Main applications include: concrete prefabrications, facade panel manufacturing, formworks
- Increased durability of the product compared to phenolic film
- High UV resistance
- High crack resistance
- Made from responsibly sourced wood in Poland

NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323, EN 324

Nominal thickness (mm)*	Number of plies (pcs) – coating included		l deviation nm)	Weight (kg/m2)	Density avg. (kg/m3)
9	7	-0,7	+0,5	7	_
12	9	-0,8	+0,6	9,3	
15	11	-0,9	+0,7	11,6	
18	13	-0,9	+0,7	14	
21	15	-1,0	+0,8	16,3	
24	17	-1,1	+0,8	18,6	
27	19	-1,8	+1,4	20,9	
30	21	-1,9	+1,5	23,3	

^{*}Other thickness available upon request

STANDARD SIZES [mm]

1250 x 2500

1500 x 2500/3000/3300

*Other sizes available upon request

Dimensional deviation as per EN 315 and EN 324

Length / width	Deviation
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm
According to norm	± 3,5 mm

Straightness and squareness deviation as per EN 315 and EN 324

± 0,1% or ± 1mm/m

COATING

Coating type	Polypropylene
Thickness	1,4 mm
Density	1,0-1,1 g/cm3
Taber Abraser	14500 (no. of cycles)
Colour	Dark grey

RELEASE OF FORMALDEHYDE (EN 717-1)

The product also meets the limit ½ E1.

BONDING QUALITY (EN 314-2)

MACHINING

CNC machining and drilling on request

ADDITIONAL INFORMATION

- General Terms of Sales available from www.sklejkapaged.pl/en
- Declaration of Performance available from www.sklejkapaged.pl/en
- Film-faced plywood in-house norms and standards available from www.sklejkapaged.pl/en

^{**}As measured at 8-12% moisture content



