

# Paged Softwood ThickPly



Znak odpowiedzialnej gospodarki leśnej

Paged Softwood ThickPly is made of selected specific thickness Polish pine and offers its users high durability and resistance to mould at a reduced total weight of the panel. Thanks to its high load-bearing capacity, smooth and uniform surface Paged Softwood ThickPly is widely used in construction and packaging industries.

### KEY BENEFITS AND APPLICATIONS

- Main application areas include: construction, interior cladding, wall sheeting and panelling, flooring and sub-flooring; packaging and industrial applications Wysokiej jakości sklejenie
- Easy to machine
- Weather and boil proof gluing
- Light and dimensionally stable
- Strong and rigid
- Made from responsibly sourced wood in Poland

**STANDARD SIZES\*** 2500x1250  
2440x1220

\*Other formats available on request

### DIMENSIONAL DEVIATION AS PER EN 315 & EN 324

Length / Width	Deviation
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm

### STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% lub ± 1mm/m
Squareness	± 0,1% lub ± 1mm/m

### NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLYS, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal thickness (mm)*	Number of plies (szt)	Standard deviation (mm)	Avg. weight (kg/m <sup>2</sup> )	Avg. density (kg/m <sup>3</sup> )
6	3	-0,6	+0,4	3,5
9	3	-0,7	+0,5	5,3
12	5	-0,8	+0,6	7
15	5	-0,8	+0,7	8,8
18	7	-1,0	+0,7	10,5
21	8	-1,0	+0,8	12,3
24	9	-1,1	+0,9	14
27	9	-1,7	+1,4	15,8
30	11	-1,9	+1,5	17,6
35	13	-1,4	+1,1	20,5
40	15	-1,6	+1,2	23,4

585\*\*

\*Other thicknesses available upon request

\*\*As measured at 8-12% moisture content

### RELEASE OF FORMALDEHYDE (EN 717-1)

E1  
The product also meets the limit ½ E1.

### BONDING QUALITY (EN 314-2)

Class 3

### MACHINING

CNC machining and drilling on request

### ADDITIONAL INFORMATION

1. General Terms of Sales available from [www.sklejkapaged.pl](http://www.sklejkapaged.pl)
2. Declaration of Performance available from [www.sklejkapaged.pl](http://www.sklejkapaged.pl)
3. Face veneer qualities according to EN 635-3.
4. BREEAM (VOC's) compliant.



Our product is made of renewable resource. Our products are characterized by low carbon footprint and are produced from certified wood, thus respecting the natural environment and the local community. The information contained in this document is intended as a guideline only and comes without warranty. We reserve the right to amend product specification sheets without notice.