





The mark of

# **Paged SidePly**

Paged SidePly is produced from high quality Baltic birch plywood coated with a polypropylene layer. The final panel offers extra protection against moisture and UV radiation, simultaneously ensuring colour fastness. Polypropylene layer is bonded with plywood by means of PUR glue. Available with a smooth or orange peel finish to match your desired application. The product is not recommended for outdoor use and any potential outdoor application is only possible after checking the coating at the application side.

#### **KEY BENEFITS AND APPLICATIONS**

- Main application areas include: Trailer walls and fit-out, horse trailers, retail shelving units, retail and commercial space fitout, furniture, transportation
- Colour fastness ≥ 6 (EN ISO 105-B02)
- Resistance to cracking
- Decorative value
- Eco-friendly (contains no halogens or plasticizers)
- Manufactured from sustainable resources in Poland

# NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal Thickness (mm)*	Number of plies (pcs)		Deviation im)	Weight (kg/m²)	Density avg. (kg/m³)
6,5	5	-0,6	+0,4	4,5	_
9	7	-0,7	+0,5	6,3	<u>_</u>
12	9	-0,8	+0,6	8,4	_
15	11	-0,9	+0,7	10,5	<u>_</u>
18	13	-0,9	+0,7	12,6	640-760**
21	15	-1,0	+0,8	14,7	_
24	17	-1,1	+0,9	16,8	_
27	19	-1,8	+1,4	18,9	<u>_</u>
30	21	-1,9	+1,5	21	

<sup>\*</sup>Other thicknesses available upon request

E1

_	 		 

- Long life-span

#### STANDARD SIZES [mm]

1250x2500 1500x2500/3000 1525x3050

\*Other formats available on request

#### **DIMENSIONAL DEVIATION AS PER EN 315 & EN 324**

Length/Width	Deviation
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm

## STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

### COATING

Type	Polypropylene
Thickness	0,15 / 0,18 mm
Colour*	White, grey
RAL	9016, 7040
Taber Test	Min. 400 (no. of cycles)

<sup>\*</sup>other colours available on request

RELEASE OF FORMALDEHYDE (EN 717-1)	BONI
RELEASE OF FORWALDETTI DE (EN 717-1)	DOM

IDING QUALITY (EN 314-2)

Class 3

#### **MACHINING**

Edge machining, CNC machining and drilling on request

## ADDITIONAL INFORMATION

- General Terms of Sales available from https://sklejkapaged.pl/en/home-page/
- Declaration of Performance available from https://sklejkapaged.pl/en/produkty/paged-sideply-2/

<sup>\*\*</sup>As measured at 8-12% moisture content







