# **Paged Colour**



STANDARD SIZES\*\* [mm]

\*With white or grev coating





The mark of

1250x2500

1500x2500/3000\*

Paged Colour is a high quality finish birch plywood made with waterproof resin and designed for both structural and nonstructural applications. It is characterised by high durability and strength, while its surface provide a decorative and easy to maintain surface.

#### **KEY BENEFITS AND APPLICATIONS**

- Main application areas include: fit-out (commercial and marine), interior cladding, furniture making and joinery,
- High durability and strength
- Hygienic and easy to maintain
- High UV resistance
- Made in Poland

- shelving, fittings for kitchens, retail space and playgrounds

### \*\*Other formats available on request

| Length / width | Deviation |
|----------------|-----------|
| < 1000 mm      | ± 1 mm    |
| 1000 – 2000 mm | ± 2 mm    |
| > 2000 mm      | + 3 mm    |

**DIMENSIONAL DEVIATION AS PER EN 315 & EN 324** 

# STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

| Deviation |  |
|-----------|--|
| n/m       |  |
| n/m       |  |
| r         |  |

## **COATING - Melamine film**

| Colour      | Thickness (g/m²) | RAL  |
|-------------|------------------|------|
| White       | 205              | 9010 |
| Silver Grey | 230              | 7046 |
| Red         | 240              | 3020 |
| Blue        | 200              | 5005 |
| Yellow      | 240              | 1021 |
| Green       | 210              | 6018 |

#### NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324

| Nominal Thickness<br>(mm)*<br>9 | Number of plies<br>(pcs) | Standard Deviation<br>(mm) |      | Weight<br>(kg/m²) | Density avg.<br>(kg/m³) |
|---------------------------------|--------------------------|----------------------------|------|-------------------|-------------------------|
|                                 | 7                        | -0,7                       | +0,5 | 6,3               |                         |
| 12                              | 9                        | -0,8                       | +0,6 | 8,4               |                         |
| 15                              | 11                       | -0,9                       | +0,7 | 10,5              | _                       |
| 18                              | 13                       | -0,9                       | +0,7 | 12,6              | - 640 760**             |
| 21                              | 15                       | -1,0                       | +0,8 | 14,7              | 640-760**               |
| 24                              | 17                       | -1,1                       | +0,9 | 16,8              | _                       |
| 27                              | 19                       | -1,8                       | +1,4 | 18,9              | _                       |
| 30                              | 21                       | -1,9                       | +1,5 | 21                |                         |

**BONDING QUALITY (EN 314-2)** 

#### **MACHINING**

### ADDITIONAL INFORMATION

<sup>\*</sup>Other thicknesses available upon request

<sup>\*\*</sup>As measured at 8-12% moisture content



